

## PREPORUČENI PROGRAMI ZA SHOFU KERAMIKU

	B/ POČETNA TEMP.	T- C/min.	T- ZADNJA TEMP.	S- DRYING	H- HOLD TIME	L-LOW COOLLING	V1- VAKUM 1	V2- VAKUM 2
BASE OPAQUE	450 C*	55 C*	960 C*	8 min.	2 min.	800 C*	450 C*	960 C*
OPAQUE 1	500 C*	55 C*	955 C*	8 min.	1 min.	800 C*	500 C*	955 C*
OPAQUE 2 (PO POTREBI)	500 C*	55 C*	950 C*	8 min.	1 min.	800 C*	500 C*	950 C*
PRVO PEČENJE	620 C*	50 C*	910 C*	10 min.	30 sec.	800 C*	620 C*	910 C*
DRUGO PEČENJE	620 C*	50 C*	904 C*	7 min.	30 sec.	800 C*	620 C*	904 C*
TREĆE PEČENJE (PO POTREBI)	620 C*	50 C*	900 C*	7 min.	30 sec.	800 C*	620 C*	900 C*
GLAZURA	620 C*	50 C*	870 C*	6 min.	30 sec.	800 C*	0 C*	0 C*